



Preformed Fabric I/O Corners

Safety Data Sheet

PFO corner: #880060201

Revision Date: 7/22/16

Version 2

Description:		Special inside corner made from non-woven, one side shortened.
Material composition:		Substrate: Modified polyester non-woven Coating: No coating
Application:		Sealing for construction corners in combination with liquid sealing.
Color:		White
Side length (approx.):		105 mm x 105 mm
Total thickness (approx.):		0,33 mm
Material weight (approx.):		2,1 g / piece
Resistance to temperature: min/max.		-30°C / + 90°C
Chemical Properties:	Resistance after storage over 7 days by room temperature in following chemicals	+ = resistant 0 = weakened - = non resistant
Hydrochloric acid 3%	Internal	+
Sulphuric acid 35%	Internal	+
Citric acid 100g/l	Internal	+
Lactic acid 5%	Internal	+
Potassium hydroxide 3% / 20%	Internal	+ / 0
Sodium hypochlorite 0,3g/l	Internal	+
Salt water (20g/l Sea water salt)	Internal	+
Certified according to DIN EN ISO 9001: 2008 Made in Germany		

Warranty: 5 years warranty for the guaranteed product qualities

Storage: cool and dry, protect against sunlight, use within 24 months after receipt.

The above technical data represent average values. The technical information and application instructions are based on our experience and present knowledge. However, it is each users own responsibility to make trials with the original substrates in order to verify the suitability of our products for the intended purpose, taking into consideration all application related parameters. Please contact NAC Products, Inc (800-633-4622) if you have any further questions.



Preformed Fabric I/O Corners

Safety Data Sheet

PFI corner: #880060101

Revision Date: 7/22/16

Version 2

Description:		Special inside corner made from non-woven, one side shortened.
Material composition:		Substrate: Modified polyester non-woven Coating: No coating
Application:		Sealing for construction corners in combination with liquid sealing.
Color:		White
Side length (approx.):		100 mm x 160 mm
Total thickness (approx.):		0,33 mm
Material weight (approx.):		2,1 g / piece
Resistance to temperature: min/max.		-30°C / + 90°C
Chemical Properties:	Resistance after storage over 7 days by room temperature in following chemicals	+ = resistant 0 = weakened - = non resistant
Hydrochloric acid 3%	Internal	+
Sulphuric acid 35%	Internal	+
Citric acid 100g/l	Internal	+
Lactic acid 5%	Internal	+
Potassium hydroxide 3% / 20%	Internal	+ / 0
Sodium hypochlorite 0,3g/l	Internal	+
Salt water (20g/l Sea water salt)	Internal	+
Certified according to DIN EN ISO 9001: 2008 Made in Germany		

Warranty: 5 years warranty for the guaranteed product qualities

Storage: cool and dry, protect against sunlight, use within 24 months after receipt.

The above technical data represent average values. The technical information and application instructions are based on our experience and present knowledge. However, it is each users own responsibility to make trials with the original substrates in order to verify the suitability of our products for the intended purpose, taking into consideration all application related parameters. Please contact NAC Products, Inc (800-633-4622) if you have any further questions.